

StaticWorx Seal Dissipative
Sealer

PRODUCT DESCRIPTION

Best results are obtained when StaticWorx Seal is applied to surfaces which are 60° F or warmer and in relative humidity conditions of between 40-65%. Remove all of the old finish or sealer with a stripping solution. Vacuum up stripping solution and rinse the floor with clean water to remove any dissolved finish residue. When used as a base coat for StaticWorx Coat, one or two coats are recommended depending on the porosity of the surface. When used as a sealer/finish on hard surfaces two or three coats will provide the optimum gloss and durability. Apply thin even coats, allowing StaticWorx Seal to dry, depending on humidity and temperature for approximately 30-45 minutes between coats. Allow two hours between the last coat of StaticWorx Seal and the first coat of StaticWorx Coat.

When used as a sealer/finish effective recoating may be achieved in the following manner. Vacuum the floor to remove any loose dirt or dust. Wash the floor with StaticWorx TriboClean or a high quality synthetic neutral cleaner, to remove dirt and soil. Apply thin even coats, allowing StaticWorx Seal to dry, for approximately 30 minutes before resumption of foot traffic. Floor surfaces should be swept with an untreated mop daily to remove abrasive loose dirt and sand. Floors should be damp mopped with StaticWorx TriboClean regularly, as needed, to remove soil, salt, and film deposits which can degrade the coatings conductive properties and gloss.

For optimum results do not apply during humid conditions, and do not dry-buff or burnish.

SAFETY INFORMATION

Health. 1
Flammability. 1
Reactivity. 0
Personal Protection. B

This material is not a hazardous mixture, as defined in 29 CFR 1919, 1200 and M.G.L. c. 111F. Safety glasses and gloves should be worn during application and handling. If ingested drink milk, water, fruit juice, and induce vomiting with oil of ipecac. In the event of eye contact flush area with water for 15 minutes. **Contact a Physician.**

For detailed information consult MSD sheet.

SPECIFICATIONS

Nonvolatile Solids	20 +/- 0.6%
Total Active	26%
Resistivity – ASTM D257	10 ⁹ Ohms ² Max/cm ² @ 40% Relative Humidity
Static Dissipation	0.02 Second
pH	8.4 – 9.0
Gloss 600	80+ @ 3 coats
Color	Translucent white
Weight Per Gallon	8.55 – 8.8
Slip Resistance (ASTM)	0.65 Minimum
Stability	1 year minimum at room temperature
Freeze/Thaw Stability	3 cycles minimum
Drying Time	30 – 45 minutes
Water Resistance	Good
Gallon Coverage (Feet ²)	1500 – 2000
Removability (Gardner)	75 cycles maximum